


harmony béton Montre et allessara a Rimuovere filigrana or.

Surface protection and mixing.





Don't forget to protect the ground with a protection tarpaulin.



Use a measuring cup and scale to measure and weigh the waxed concrete.

Dosage: 250 ml of resin for 1 kg of powder.




Roll the bucket of waxed concrete before opening it to decompact it.



After measuring the quantity of resin required, pour it first into an empty bucket, then add the powder.



 $\mbox{\rm Mix}$ everything at medium speed until obtaining a homogeneous paste.





1 st layer





Use a knife to be coated or a









Step: Implementation of waxed concrete on the wall.

harmony béton Rimuovere filigrana ora

2 nd layer




Before applying the 2nd coat, remove all pollutions and eliminate the forgotten defects.



Apply the 2nd layer of waxed concrete.

It is not necessary to sand between the 1st and 2nd coats.




Return as and when on the waxed concrete which begins to dry in order to iron it with the trowel.




The shoeing allows to increase the resistance, creating effects of colors and of materials.

Ferrer consists in ironing several times the smoother as flat as possible by exerting more and more pressure as soon as the waxed concrete is sufficiently hard.



The shoein can also be done with a flat stainless steel smooth by small circular and regular movements.



To reduce the color effects of the shoeing, use the plastic smoother.

Step: Implementation of waxed concrete on the wall.



Sanding



24 hours after the application of the second layer of waxed concrete, sand the surface with a disc of 80 then 120.



To facilitate sanding at the edges or corners, use the sanding block.



Sanding cleares the waxed concrete and accentuates the strike effects.

The shades of white will disappear with the varnish. After sanding, dust off before varnishing.